
Trade Name: ASTRO HBP PRIMER
HIGH BUILD PRIMER

Compatible with our intumescent paint

High Build & Quick Drying

Red, White or Grey

Solvent or water based options

Brush, Roller or Spray

Suitable as a general use metal primer



Description

A High Build Quick Drying corrosion resistant metal primer for structural steel and cast iron. Contains high durability resin binders, light fast pigments and a high concentration of zinc phosphate.

Compatible with ASTRO ISS Paint and most other intumescent paint systems, epoxy and conventional paints.

Suitable for application in Steel Fabricator's shops or on site. Will protect exposed structural steel during construction as well as protecting internal steelwork thereafter.

May be overcoated with our intumescent paint systems as well as epoxy, conventional gloss, eggshell, acrylic and vinyl paint finishes.

Availability

ASTRO HBP Primer is available in 2.5 litre and 5 litre containers.

To Order & Specify

We are happy to provide specifications and quotations - please use our [specification form](#) to ensure we cover all aspects of your fire protection and decorative requirements in our quote. We accept any order size.

Prior to application the contractor should contact the Astroflame Technical Department (see above) to obtain a basecoat application schedule.

Application

Single Pack. Suitable for brush, roller or airless spray application. Do not stir.

Airless Spray -Graco 1500, 5000 or equivalent.
Thinners - Do not thin.
Solvent based -Clean equipment with white spirit.
Water based -Clean equipment with water.

Max. Relative Humidity 80%.
Min.Temperature 6° C.
Min.Steel Temperature 3° C above Dew Point.

Remove weld spatter, grind down weld seams and sharp edges. Blast clean to SA2½ Swedish Standard. If impractical remove all rust and millscale with hand powertools, avoiding polishing the surface. Prime before rust starts to re-form. Surfaces should be free from dust, dirt and grease.

Volume solids50%
Dry film thickness75 microns.
Theoretical coverage 6m sq/litre.
Colours..... Grey/ white /red.

Minimum drying times:

	Water Based	Oil Based
Touch Dry	2 hours.	6 hours.
Re-Coat	4 hours.	12 hours.

Health and Safety

Observe all normal health and safety precautions for painting including ventilation, hygiene and masks and protective clothing as appropriate.

As part of our policy of ongoing improvements, we reserve the right to modify, alter or change product specifications without giving notice. Product illustrations are representations only. All information contained in this document is provided for guidance only, and as ASTROFLAME FIRESEALS LTD has no control over the installation methods of the products, or of the prevailing site conditions, no warranties expressed or implied are intended to be given as to the actual performance of the products mentioned or referred to, and no liability whatsoever will be accepted for any loss, damage or injury arising from the use of the information given of products mentioned or referred to herein.

The above information to the best of our knowledge is true and accurate and based upon current test data and is supplied for your guidance only. Customers should satisfy themselves to the suitability of the product in its intended use and no guarantee is given or implied since the conditions of actual use are beyond our control. ASTROflame (Fireseals) Ltd, disclaim any liability for loss, damage or other expense arising from the use of information, data or products mentioned or referred to and reserve the right to change any details or specifications without notice.

Astroflame (Fire Seals) Ltd. Intumescent House
Unit 8, The IO Centre, Stephenson Road, Segensworth
FAREHAM, ENGLAND PO15 5RU

tel 0800 023 2482
(01329 844500)

fax 0800 023 2483
(01329 844600)

intl
tel +44 1329 844500

fax +44 1329 844600

email sales@astroflame.com